AVORIO

BEIGE

ATLANTIC TILE STONE

Italian Porcelain 6x24 Honed & Lappato, 12x24 Honed & Lappato, 2x2 Mosaics, 2.75x24 Honed & Lappato Bullnose

SHADE VARIATION

AMERICA

V3 - Moderate Variation While the colors present on a single piece of tile will be indicative of the colors to be expected on the other tiles, the amount of colors on each piece may vary significantly. For example "that little bit of color" on one piece of tile may be the primary color on the next piece.



WEAR CODE

Rated for all residential and commercial applications.

	PERFORMANCE DATA		THIC	KNESS	10 m m	
Ē	CHARACTERISTIC	NORMS		RESULTS		
	Water Absorption	ISO 10545-3	:	≤ 0.5%		
	Deep Abrasion	ISO 10545-6	4	< 175 mm	3	
	PEI Abrasion Resistance (Glazed)	ISO 10545-7	[NA		
	Breaking Strength	ISO 10545-4	ž	≥ 35 N/mi	m2	
	Dynamic Coefficient of Friction Wet AcuTest		2	≥ 0.42 (matte)		
	Dimensions Range	ISO 10545-2	(Conforms	3	
	Frost Resistance	ISO 10545-12		Frost Proc	of	
	Chemical Resistance - Household Chemicals	ISO 10545-13	(Conforms	3	
	Chemical Resistance - Low Concentration of Acids & Bases	ISO 10545-13	(Conforms		
	Thermal Shock Resistance	ISO 10545-9		Resistant		
	Resistance to Stains	ISO 10545-14	(Cleanable)	
	Crazing Resistance of Glazed Tiles	ISO 10545-11		Resistant		



blend.

Per ANSI standard A108.02,4.3.82, joints on tiles longer than 18" should not be staggered more than 1/3 the length of the tile. Always inspect materials prior to installations. Always mix 2-3 cartons at a time while installing to insure the best





www.tileamerica.com





ANTRACITE



NERO

