




ATLANTIC STONE

An Italian porcelain collection whose name reflects the strength and durability of the stone along our shorelines. Atlantic Stone offers the look of quartzite with strong white veins in 5 gorgeous tones: Avorio, Beige, Grigio, Antracite and Nero. Offered in both a matte and lappato (semi-polished) finish.

SIZE	COLOR				
	avorio	beige	grigio	antracite	nero
2.75x24 Bullnose Finish: matte & lappato Thickness: 10 mm					
6x24 Finish: matte & lappato Thickness: 10 mm					
12x24 Finish: matte & lappato Thickness: 10 mm					
12x12 Mosaic Finish: matte & lappato Thickness: 10 mm					

ATLANTIC STONE TECHNICAL INFORMATION

SHADE VARIATION



V3 - Moderate Variation

While the colors present on a single piece of tile will be indicative of the colors to be expected on the other tiles, the amount of colors on each piece may vary significantly. For example “that little bit of color” on one piece of tile may be the primary color on the next piece.

WEAR CODE

5 - Rated for all residential and commercial applications.

PERFORMANCE DATA

CHARACTERISTIC	NORMS	RESULTS
Water Absorption	ISO 10545-3	≤ 0.5%
Deep Abrasion	ISO 10545-6	< 175 mm ³
PEI Abrasion Resistance (Glazed)	ISO 10545-7	NA
Breaking Strength	ISO 10545-4	≥ 35 N/mm ²
Dynamic Coefficient of Friction Wet	AcuTest	≥ 0.42 (matte)
Dimensions Range	ISO 10545-2	Conforms
Frost Resistance	ISO 10545-12	Frost Proof
Chemical Resistance - Household Chemicals	ISO 10545-13	Conforms
Chemical Resistance - Low Concentration of Acids & Bases	ISO 10545-13	Conforms
Thermal Shock Resistance	ISO 10545-9	Resistant
Resistance to Stains	ISO 10545-14	Cleanable
Crazing Resistance of Glazed Tiles	ISO 10545-11	Resistant

NOTES

It is not recommended to stagger any tile longer than 18” more than 1/3 the length of the tile.

Minimum grout joint recommendation: 1/8”

Always inspect materials prior to installation.

Always mix 2-3 cartons at a time while installing to insure the best blend.

All product images are representation only. Variation in color and shading is to be expected. Final selection should be made from actual tile samples.