T | L E 🔶 A M E R I C A[®]



Key Product Features:

Can even be added after the tile is installed!

Seamless Application: The 8-foot length of the jolly liner allows for a seamless transition between adjoining tile and stone surfaces, eliminating the need for grout lines.

Versatile Installation: The product can be installed in four ways – as a cap, liner, corner, or tile trim finishing piece, providing flexibility for different design requirements.

Flexible Material: The quarter round is composed of a flexible and durable composite material, making it ideal for commercial or residential applications.

Low-Cost Easy Installation: The lightweight and flexible design of the liner makes it easy to handle and install, saving time and effort for contractors and DIY enthusiasts.

Wet Saw Cutting: It can be easily cut with a wet saw, making customization and fitting simple during installation. Perfect for Wet Wall Applications: Designed for use in wet areas and can be used in various wet-wall applications, such as shower walls, tub surrounds, and kitchen backsplashes.

Permanently Sealed: The liner has a patented antimicrobial scratch-resistant surface that protects against fingerprints, mold, and mildew, ensuring lasting beauty and easy maintenance.

SIZES:	COLOR		
1∕2 " x 96 " Matte	Bright White	Cool Gray	Black
1⁄2 " x 96 " Polished			

$\top \mid \mathsf{L} \vDash \diamondsuit \land \mathsf{A} \land \mathsf{M} \vDash \mathsf{R} \lor \mathsf{C} \land \mathsf{A}^{\circ}$

TECHNICAL INFORMATION

SANDGATE JOLLY 8'

SHADE VARIATION

V1 - Uniform Appearance Differences among pieces from the same production run are minimal.

WEAR CODE

Class 1 Rated for wall application only THICKNESS

1/4 Round

PERFORMANCE DATA

CHARACTERISTIC	NORMS	RESULTS		
Breaking Strength	ASTM C6481	130-170 lbs.		
		(¼" nominal thickness)		
Facial Dimensions	ASTM C499	Average ≤ 4.0%		
		Range/Max ≤ 0.6%		
Wedging	ASTM C502	≤ 0.6%		
Water Absorption	ASTM C373	0.73%-1.21%		
24 hr. Resistance to Household				
Chemical Substances	ASTM C650	No effect. Ten (10)		
		cleaning chemicals, two (2)		
		base concentrations and		
		two (2) acid concentrations		
24 hr. Resistance to Staining	ASTM C1378	No visual effect. Six (6)		
		staining agents and two (2)		
		cleaning procedures.		
Surface Burning	ASTM E84-95b	Class B		
Surface Resistivity	Questech	non-conductive		
NOTES				
N/A				